



---

*Institute of Paper Science and Technology  
Atlanta, Georgia*

---

**IPST Technical Paper Series Number 847**

**Pyrolysis Mass Spectral Characterization of Wood from CAD-Deficient Pine**

**J. MacKay and D.R. Dimmel**

**April 2000**

**Submitted to  
Journal of Wood Chemistry and Technology**

*Copyright® 2000 by the Institute of Paper Science and Technology*

*For Members Only*

## INSTITUTE OF PAPER SCIENCE AND TECHNOLOGY PURPOSE AND MISSIONS

The Institute of Paper Science and Technology is an independent graduate school, research organization, and information center for science and technology mainly concerned with manufacture and uses of pulp, paper, paperboard, and other forest products and byproducts. Established in 1929 as the Institute of Paper Chemistry, the Institute provides research and information services to the wood, fiber, and allied industries in a unique partnership between education and business. The Institute is supported by 52 North American companies. The purpose of the Institute is fulfilled through four missions, which are:

- to provide multidisciplinary graduate education to students who advance the science and technology of the industry and who rise into leadership positions within the industry;
- to conduct and foster research that creates knowledge to satisfy the technological needs of the industry;
- to provide the information, expertise, and interactive learning that enables customers to improve job knowledge and business performance;
- to aggressively seek out technological opportunities and facilitate the transfer and implementation of those technologies in collaboration with industry partners.

## ACCREDITATION

The Institute of Paper Science and Technology is accredited by the Commission on Colleges of the Southern Association of Colleges and Schools to award the Master of Science and Doctor of Philosophy degrees.

## NOTICE AND DISCLAIMER

The Institute of Paper Science and Technology (IPST) has provided a high standard of professional service and has put forth its best efforts within the time and funds available for this project. The information and conclusions are advisory and are intended only for internal use by any company who may receive this report. Each company must decide for itself the best approach to solving any problems it may have and how, or whether, this reported information should be considered in its approach.

IPST does not recommend particular products, procedures, materials, or service. These are included only in the interest of completeness within a laboratory context and budgetary constraint. Actual products, materials, and services used may differ and are peculiar to the operations of each company.

In no event shall IPST or its employees and agents have any obligation or liability for damages including, but not limited to, consequential damages arising out of or in connection with any company's use of or inability to use the reported information. IPST provides no warranty or guaranty of results.

The Institute of Paper Science and Technology assures equal opportunity to all qualified persons without regard to race, color, religion, sex, national origin, age, disability, marital status, or Vietnam era veterans status in the admission to, participation in, treatment of, or employment in the programs and activities which the Institute operates.

## PYROLYSIS MASS SPECTRAL CHARACTERIZATION OF WOOD FROM CAD-DEFICIENT PINE

J. MacKay and D. R. Dimmel,  
Institute of Paper Science and Technology, 500 10th Street NW  
Atlanta, Georgia 30318, U.S.A. E-mail: john.mackay@ipst.edu

J. J. Boon  
FOM Institute for Atomic and Molecular Physics, Kruislaan 407, 1098 SJ  
Amsterdam, The Netherlands E-mail: boon@amolf.nl

### ABSTRACT

An extremely low level of the cinnamyl alcohol dehydrogenase (CAD) enzyme activity in a mutant loblolly pine tree leads to a different pool of precursors for lignin production. Characterization of CAD-deficient wood by pyrolysis mass spectroscopy indicates significant increased levels of dihydroconiferyl alcohol, not usually considered a lignin subunit. Also, in comparison to normal pine lignin, the CAD-deficient lignin has increased levels of coniferaldehyde, the substrate of CAD, and of *p*-coumaryl alcohol, along with greatly decreased levels of coniferyl alcohol. These findings were consistent in trees of different ages and confirm that there is considerable plasticity in the biosynthesis of lignin, based upon the utilization of structures beyond the traditional definition of lignin precursors.

### INTRODUCTION

Loblolly pines with unusual lignin can be obtained through crosses of trees that have a mutant gene, the *cad-nl* allele, found in breeding stocks.<sup>1,2</sup> The *cad* gene encodes an enzyme, cinnamyl alcohol dehydrogenase (CAD), that is normally required in lignin biosynthesis.<sup>3,4</sup> The *cad-nl* allele can be used in well-defined crosses to produce trees that are almost totally CAD-deficient (homozygous for the *cad-nl* allele) or partially CAD-deficient (heterozygous for the *cad-*

*n1* allele). Totally CAD-deficient (referred to hereafter as CAD-) trees are more easily pulped than normal trees.<sup>5</sup> The reasons behind this increased reactivity are of high interest to scientists attempting to develop superior sources of pulpwood.

Lignins from completely CAD- trees are built up from unusual monomers. Analysis of a CAD- milled wood lignin (MWL) by NMR indicated the presence of three unusual monomers in significant amounts. The monomers are coniferaldehyde (1), vanillin (2), and dihydroconiferyl alcohol (3) (Fig. 1).<sup>2</sup> The increase in dihydroconiferyl alcohol (DHCA) was dramatic and unexpected. While solution NMR is a powerful characterization tool, it requires isolation of lignin and, thus, may give an inadequate representation of the entire lignin fraction in its native state. For, example the NMR characterization of pine CAD- lignin used an MWL sample that represented less than 20% of the total lignin.<sup>2</sup> In addition, scientists disagree on whether the prolonged ball-milling required to isolate MWL lignin alters the structure of the lignin.<sup>6</sup> Finally, the results obtained by NMR were based upon the analysis of a single tree. Given the significance of the NMR conclusion and the noted limitations, we sought to verify the high levels of DHCA in whole-wood samples, and with more than one tree, by other analyses.




Figure 1. Building blocks for lignin production in CAD-deficient trees.

Application of thioacidolysis techniques to whole-wood samples showed that the lignin in totally CAD- trees, relative to normal pinewood, contained much higher levels of DHCA units and C<sub>5</sub>-linkages, and correspondingly less C<sub>β</sub>-O<sub>4</sub> linkages.<sup>7</sup> Such linkage distribution is consistent with lignin biosynthesis theory, in which lignin is produced by coupling delocalized phenolate radicals. With the

type of monomers available in the CAD- case, there are greatly reduced opportunities to couple at a C $\beta$ -site. We have applied pyrolysis mass spectroscopy (PYMS) to the same type wood samples studied by the thioacidolysis techniques. PYMS can provide fingerprinting information on lignin in the wood matrix.<sup>8</sup> Molecular-level information is obtained on the polysaccharide and lignin distribution in microgram size wood particles in a single analytical run. The temperature-resolved data-acquisition process separates loosely bound from more condensed cross-linked fractions. Specific information is obtained on the monomeric and oligomeric units in lignin.<sup>9, 10</sup>

### Mass Spectral Techniques

PYMS is a powerful technique for studying whole-wood samples. Homogenized particulate samples are placed on a resistively heatable Pt/Rh filament mounted on a direct-insertion probe inside the ion source of a mass spectrometer. The filament is heated rapidly and the sample vaporized and pyrolyzed over a discrete time period. Spectra are continuously recorded as the sample vaporizes. The heating and subsequent ionization cause polymeric compounds to liberate (at least some of) their monomeric components; in essence, we see the mass spectra of the low-molecular-weight components. Several modes of sample ionization are available; we employed electron ionization (EI) and chemical ionization (CI). If a relatively low (i.e., 16 eV) EI voltage is employed, molecular ion fragmentation is minimized. This is an important consideration when dealing with samples that are mixtures of substances. The spectra become very complex when fragment ions of one compound overlap with molecular ions of another.

Chemical ionization has the advantage of providing a "soft" molecular ionization, one that typically does not provide much fragmentation. The CI gas employed in our studies was ammonia; the NH<sub>3</sub> molecules are ionized and collide with other NH<sub>3</sub> molecules to generate NH<sub>4</sub><sup>+</sup> ions that then add directly or deliver H<sup>+</sup> to the compound to give [M + 18 (NH<sub>4</sub>)]<sup>+</sup> and/or [M + 1 (H)]<sup>+</sup> ions. Significant amounts of fragment ions can result, for example, when a protonated molecule can lose a simple molecule, such as H<sub>2</sub>O, and generate very stable cations in the process. This process is more prominent when the internal energy of the neutral molecule is relatively high due to thermal processes on the filament.

Another technique employed in this study was PYMS/MS. Here again, a low-voltage EI ionization of the vaporized sample generates abundant amounts of molecular ions. The magnet is set to pass one ion, i.e.,  $m/z$  180, into a chamber containing helium gas. The ion is accelerated from the ion source at 8 kV and undergoes high-energy collisions with the helium gas to generate fragment ions that are then passed through an energy-sector analyzer. The latter is scanned to show the distribution of the fragment ions. In essence, we are recording mass spectra of MS-separated ions and confirming component structures present in the mixture. For example, the  $m/z$  180 of coniferyl alcohol ( $\text{ArCH=CHCH}_2\text{OH}$ ) will show characteristic fragmentation ions that will be different from the  $m/z$  180 of dihydroconiferyl aldehyde ( $\text{ArCH}_2\text{CH}_2\text{CHO}$ ). Knowing these fragmentation patterns in advance allows for accurate assignment of the  $m/z$  180 ion in a spectrum.




## **RESULTS AND DISCUSSION**

### **EI-PYMS Characterization**

Wood samples from totally CAD- and normal loblolly pine seedlings and from one 12-year-old CAD-deficient tree were vaporized/pyrolyzed over a temperature range of 160-640°C and subjected to 16 eV EI ionization. The respective mass scans were time-integrated to provide the partial spectral data shown in Fig. 2. The normal wood samples had a dominant signal at  $m/z$  180 that corresponds to coniferyl alcohol (CA).<sup>10,11</sup> The CAD- samples showed  $m/z$  178, 180, and 182 signals of comparable intensities. The former signal corresponds to coniferaldehyde and the latter to DHCA. Several other lignin-related signals are also observed, including  $m/z$  124 (fragment ion of CA), 137 (fragment ion of CA), 150 (ethenyl-methoxyphenol), 152 (vanillin), and 164 (propenyl-methoxyphenols).

The relative ratios of the signals of interest (Table 1) were calculated from the two spectra shown in Fig. 2. The relative signal intensities probably do not represent the actual ratios of the components in the samples due to differences in mass-spectral response. The only condition where intensities equal component ratios is when each component ionizes and fragments to the same extent; this is not likely, except for closely related isomers, such as *cis/trans* alkenes, and *m/p*-

Table 1. Relative area ratios observed by EI-PYMS for normal and CAD- woods.

Wood	Relative Area Ratios of Select Ions		
	 178	 180	 182
Normal	0.33	1	0.05
CAD-	0.90	1	0.60




Figure 2. Partial PYMS EI mass spectra representative of results obtained with normal and CAD- wood. The Y-axis is the relative abundance; 100 represents the most abundant signal in the spectrum.

substituted benzenes, etc. If authentic samples were available, known mixtures could be prepared and subjected to the PYMS conditions to develop relative responses. This was not done in our study. Therefore, all that can be concluded from

the data in Table 1 is that the ratios of components are significantly different for the normal and CAD- woods. Much lower coniferyl alcohol and more dihydroconiferyl alcohol (DHCA) are present in the CAD- wood.

We observed the same significant increase in DHCA  $m/z$  182 signal both in the CAD-deficient seedlings and the 12-year-old tree. This finding indicates that high levels of DHCA are not specific to one individual or to a developmental stage of the tree. A multivariate analysis (not shown) clearly discriminated between the normal and CAD- wood types. Coniferyl and dihydroconiferyl alcohol concentrations were the strongest and practically the only important changes. This analysis also revealed a smaller increase of  $m/z$  150, 107, and 94 in the CAD-woods, usually associated with *p*-coumaryl alcohol subunits (H units). A similar finding regarding H units was detected by thioacidolysis in CAD- pine seedlings of this same family.<sup>7</sup>

The incorporation of coniferaldehyde residues into the lignin of plants or trees with a low-level CAD activity has been well documented and demonstrated with several techniques including PYMS.<sup>12-15</sup> In contrast, the utilization of DHCA as a lignin precursor appears, so far, unique to CAD- pine and may be the result of a more severe decrease in enzyme activity than in other studies.

### **Ammonia CI-PYMS Characterization**

Samples of totally CAD- and normal loblolly pine wood were also analyzed by CI-PYMS to verify the  $m/z$  182 signal assignment is, indeed, due to DHCA. The vaporized samples were subjected to ammonia chemical ionization and the mass spectra time-integrated over the temperature range 160-640°C to provide the partial spectral data shown in Fig. 3. Both wood samples have a large signal from 1,6-anhydroglucose, a cellulose fragment.<sup>8</sup> As for lignin-related signals, the normal wood shows a strong  $m/z$  163 signal that corresponds to protonation of coniferyl alcohol, followed by loss of water (Fig. 4).<sup>11</sup> The CAD- wood shows a much lower  $m/z$  163 signal and more intense  $m/z$  196 and 200 signals. The latter signals correspond to ammonium ion addition to coniferaldehyde and DHCA, respectively (Fig. 4). Here again, the data provide qualitative, rather than quantitative information.






Figure 3. PYMS ammonia CI mass spectra of normal and CAD- wood. The Y-axis is the relative abundance; 100 represents the most abundant signal in the spectrum.




Figure 4. Ammonia CI reactions with lignin structures of interest.

## PYMS/MS Characterization

Structure assignments for the ions observed in the EI-PYMS were confirmed by PYMS/MS. The  $m/z$  180 ion was shown to produce  $m/z$  152, 137 (strong), and 124 ions that are characteristic of coniferyl alcohol. The  $m/z$  182 ion was shown to produce  $m/z$  164, 152, 137 (strong), and 122 ions that are characteristic of dihydroconiferyl alcohol. Figure 5 presents some possible structures for these ions.




Figure 5. Possible ion structures observed in the mass spectra of normal and CAD- wood.

The important point of the PYMS/MS data is that the fragment ions from the  $m/z$  178, 180, and 182 ions are the expected ions from the proposed lignin structures and not related to carbohydrate or other component structures. In addition, the ions are the same in both normal and CAD- wood, meaning that there was a shift in relative distributions of lignin monomeric compounds, rather than new (non lignin) compounds being formed by the CAD- plant.

## CONCLUSIONS

Whole-sample pyrolysis mass spectra of normal and totally CAD-deficient loblolly pines indicate that the latter has a much higher relative level of dihydroconiferyl alcohol, and somewhat higher level of coniferaldehyde. The extremely low-level CAD enzyme in pine trees that carry the *cad-n1* allele clearly lead to important changes in the subunit composition and structure of lignin. These changes, first observed in an isolated MWL by FTIR,<sup>1</sup> NMR,<sup>2</sup> and UV,<sup>16</sup> have now

been confirmed by analyses that do not require lignin isolation. The NMR analysis of MWL showed that DHCA is a significant lignin subunit in the CAD- trees. This finding has now been confirmed with thioacidolysis<sup>7</sup> and PYMS of wood samples. These later methods have furthermore demonstrated that this interesting finding is consistent among CAD- deficient trees and that it does not appear to be dependent on age or growth conditions. Similarly, the dominant features of the FTIR and UV spectra of MWL from a CAD- tree were also observed in the spectra obtained with samples from several seedlings or trees using finely ground wood (FTIR<sup>1</sup>) or thin wood sections (UV-microphotospectrometry<sup>17</sup>). Overall, results obtained with wood samples have been in strong agreement with those from isolated lignin samples.

The utilization of DHCA as a lignin precursor constitutes one more example of the considerable metabolic plasticity of lignin biosynthesis in plants.<sup>11,13</sup> Interestingly, the increased incorporation of DHCA has only been reported in pine, so far; a mechanism for its formation has yet to be demonstrated. However, the various analyses of totally CAD- trees clearly demonstrate that DHCA is intimately linked to other lignin subunits and, therefore, functions as a *bona fide* lignin precursor in this case.<sup>2,7,18</sup> Although unexpected, the incorporation of DHCA points to greater opportunity to manipulate lignin structure than previously anticipated.

## **EXPERIMENTAL**

### **Plant material**

Loblolly pine seedlings of a selfed family obtained from a *cad-nl* heterozygous mother-tree (7-56) were grown for 10 months under standard greenhouse conditions. The *cad* genotype (CAD- or wild type) of each seedling was determined using RAPD markers as a fingerprinting method.<sup>1</sup> Wood was isolated from randomly selected seedlings related to two wild-type (30.4% and 31% lignin) and two CAD- (24.9% and 27.5 % lignin). Identification and characterization of a 12-year-old CAD- tree (28% lignin) were described.<sup>2,16</sup> Wood samples were air dried and extracted with water, followed with acetone. Aliquots of the samples were homogenized in a glass minimortar using water as a suspension fluid.

## Instrumentation

**Pyrolysis-MS.** PYMS analyses (in direct temperature-resolved MS mode) were performed according to Pillonel et al.<sup>19</sup> Between 5 and 10  $\mu\text{g}$  of an aqueous wood particle suspension was applied to the wire and dried *in vacuo*. The pyrolysis was carried out using an insertion probe equipped with a resistively heated Pt/Rh (9/1) filament loop (100  $\mu\text{m}$  diameter) inserted inside the ion source of a JEOL SX-102A double-focusing mass spectrometer (reversed geometry B/E). Ionization was performed under electron ionization (EI) or ammonia chemical ionization conditions (CI). The mass spectrometer was operated at 10 kV. The mass range was scanned from  $m/z$  20-1000 (EI) or  $m/z$  60-1000 (CI) with a cycle time of 1 second. Data were acquired and processed using the JEOL MP7000 data system. Data were exported to a high-speed computer for further data processing by multivariate analysis. Discriminant analysis (double-stage principal-component analysis<sup>20</sup>) was performed on the data to identify sets of mass peaks whose intensity was significantly different between the various samples. Both FOMpyroMAP and Chemometriks programs<sup>21</sup> were used for this analysis.

**Pyrolysis MS/MS.** The pyrolysis conditions were similar to the PYMS described above. A home-built collision cell behind the magnet just before the electron sector allowed the performance of MIKES (Mass analyzed Ion Kinetic Energy Spectroscopy) studies of selected ions. The analysis had to be performed in a multichannel-averaging mode of the data acquisition for reasons of sensitivity. Helium was used as the collision gas. The analysis was performed on  $m/z$  178, 180, and 182 obtained by low voltage EI.

## ACKNOWLEDGEMENTS

This work was partially supported by the United States Department of Agriculture, Grant No. 97-35103-4796. The mass spectrometric work is part of the approved research program FOM 28 of the Stichting FOM (Foundation for Fundamental Research of Matter) which is subsidized by the Netherlands Organization for Scientific Research (NWO). Mr. Jerre van der Horst and Mr. Gert Eijkel are acknowledged for their technical assistance with the MS and multivariate analysis work.

## REFERENCES

1. MacKay, J. J., O'Malley, D. M., Presnell, T., Booker, F. L., Campbell, M. M., Whetten, R. W., and Sederoff, R. R. Inheritance, gene expression and lignin characterization in a mutant pine deficient in cinnamyl alcohol dehydrogenase. *Proc. Natl. Acad. Sci. USA*, 94, 8255-8260 (1997).
2. Ralph, J., MacKay, J. J., Hatfield, R. D., O'Malley, D. M., Whetten, R. W., and Sederoff, R. R. An abnormal lignin in a mutant loblolly pine (*Pinus taeda* L.). *Science*, 277, 235-239 (1997).
3. O'Malley, D., Porter, S., and Sederoff, R. R. Purification, characterization and cloning of cinnamyl alcohol dehydrogenase in loblolly pine (*Pinus taeda* L.). *Plant Physiol.*, 98, 1364-1371 (1992).
4. MacKay, J. J., Liu, W., Whetten, R. W., Sederoff, R. R., and O'Malley, D. M. Genetic analysis of cinnamyl alcohol dehydrogenase (CAD) in loblolly pine: single gene inheritance, molecular characterization and evolution. *Molecular and General Genetics*, 247, 537-545 (1995).
5. Dimmel, D. R., MacKay, J. J., Althen, E. M., and Parks, C. Pulping and bleaching of CAD-deficient wood," *J. Wood Chem. Technol.*, submitted.
6. Hon, D. N.-S. Mechanochemical reactions of lignocellulosic materials. *J. Appl. Polymer Sci. (Appl. Polymer Symp.)* 37(1), 461-481 (1983).
7. Lapierre, C., Pollet, B., MacKay, J. J., Dimmel, D. R., and Sederoff, R. R. Lignin structure in a mutant pine deficient in cinnamyl alcohol dehydrogenase. *Proceed. Intern. Symp. Wood and Pulping Chem.*, Yokohama, Japan, June 7-10, 1999, Vol. 1, p. 520-523.
8. Boon, J. J. Analytical pyrolysis mass spectrometry: new vistas opened by temperature-resolved in-source PYMS. *International Journal of Mass Spectrometry and Ion Processes*, 118/119, 755-787 (1992).
9. Van der Hage, E. R. E., Weeding, T. L., and Boon, J. J. Mass spectrometry of natural and synthetic lignin polymers: on the detection of coumaryl units by in-source pyrolysis mass spectrometry. In: R. P. Newton and T. J. Walton (Eds.), *Applications of Modern Mass Spectrometry in Plant Science Research (Proceedings of the Phytochemical Society of Europe)*, Oxford, Clarendon Press, p.117-138 (1996).
10. Van der Hage, E. R. E., Boon, J. J., Steenvoorden, R. J. J. M., and Weeding, T. L. Resonance-enhanced multiphoton ionization mass spectrometric analysis of lignin using laser pyrolysis with entrainment into supersonic jet. *Anal. Chem.* 66: 543-550 (1994).

11. Van der Hage, E. R. E., Weeding, T. L., and Boon, J. J. Ammonia chemical ionization mass spectrometry of substituted phenylpropanoids and phenylalkyl phenyl ethers. *J. Mass Spectrometry*, 30, 541-548 (1995).
12. Baucher, M., Chabbert, B., Pilate, G., van Doorselaere, J., Tollier, M.-T., Petit-Conil, M., Cornu, D., Monties, B., van Montagu, M., Inzé, D., Jouanin, L., and Boerjan, W. Red xylem and higher lignin extractability by down-regulating cinnamyl alcohol dehydrogenase in poplar (*Populus tremula x Populus alba*). *Plant Physiol.*, 112, 1479-1490 (1996).
13. Halpin, C., Knight, M. E., Foxon, G. A., Campbell, M. M., Boudet, A. M., Boon, J. J., Chabbert, B., Tollier, M.-T., and Schuch, W. Manipulation of lignin quality by downregulation of cinnamyl alcohol dehydrogenase. *Plant Journal*, 6, 339-350 (1994).
14. Ralph, J., Hatfield, R. D., Piquemal, J., Yahiaoui, N., Pean, M., Lapierre, C., Grima-Pettenati, J., and Boudet, A. M. NMR characterization of altered lignins extracted from tobacco plants down-regulated for lignification enzymes cinnamyl-alcohol dehydrogenase and cinnamoyl-CoA reductase. *Proc. Nat. Acad. Sci.*, 95, 12803-12808 (1998).
15. Lapierre, C., Pollet, B., Petit-Conil, M., Toval, G., Romero, J., Pilate, G., Leple, J.-C., Boerjan, W., Ferret, V., De Nadai, V., and Jouanin, L. Structural alteration of lignins in transgenic poplars with depressed cinnamyl alcohol dehydrogenase or caffeic acid O-methyltransferase activity have an opposite impact on the efficiency of industrial kraft pulping. *Plant Physiol.*, 119, 152-163 (1999).
16. MacKay, J. J., Presnell, T., Jameel, H., Taneda, H., O'Malley, D. M., and Sederoff, R. R. Modified lignin and delignification with a CAD-deficient loblolly pine. *Holzforschung*, 53, 403-410 (1999).
17. MacKay, J. J. and Akin, D. I., unpublished data.
18. Whetten, R. W., MacKay, J. J., and Sederoff, R. R. Recent advances in lignin biosynthesis. *Ann. Rev. Plant Physiol. & Plant Mol. Biol.*, 49, 585-609 (1998); Sederoff, R. R., MacKay, J. J., Ralph, J., and Hatfield, R. D. Unexpected variation in lignin. *Curr. Opin. In Plant Biol.*, 2: 145-152 (1999).
19. Pillonel, C., Mulder, M. M., Boon, J. J., Forster, B., and Binder, A. Involvement of cinnamyl-alcohol dehydrogenase in the control of lignin formation in *Sorghum bicolor* L. Moench. *Planta*, 185, 538-544 (1991).
20. Klap, V. A., Boon, J. J., Hemminga, M. A., and Van Soelen, J. Assessment of the molecular composition of particulate matter exchanged between Saeftinghe marsh (southwest Netherlands) and the adjacent water system. *Marine Chemistry*, 54, 221-243 (1996).
21. Hoogerbrugge, R., Willig, S. J., and Kistemaker, P. G. Discriminant analysis by double stage principal component analysis. *Anal. Chem.*, 55, 1710-1712 (1983).